

August 31, 2001
Date

Don Korman
Express Mail Label No.:
EL846221994 US

-1-

TITLE OF THE INVENTION

METHOD OF MANUFACTURING MAGNETIC RECORDING
MEDIUM AND THE MAGNETIC RECORDING MEDIUM

Specs

5 BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a method of manufacturing a recording medium and the recording medium for use in a magnetic recording and reproduction device such as a hard disk drives serving as a secondary storage device of computers.

2. Description of the Related Art

sub B In recent years, there is an increasing need of high-density recording in magnetic storage device known such as hard disk drives. In such hard disk drives for high-density recording, it is necessary to reduce the magnetic spacing, which is a space formed between a magnetic head provided in the magnetic disk drives and the surface of a magnetic disk serving as a recording medium in the main body of the hard disk drives, as much as possible. In other words, the gap between the magnetic head and the magnetic disk surface, scanned by the magnetic head, should be as small as possible.

Fig. 1 is a schematic diagram showing a magnetic disk drive 100 including a magnetic head 120 and a rotatable magnetic disk 110 of the related art. Fig. 1 is illustrated in an enlarged view; so as to clearly show the layered structure of the magnetic disk 110 and magnetic spring S.

Referring to Fig. 1, the magnetic disk has a multilayered structure including a substrate 111, an underlayer 113 formed on the substrate 111, and a magnetic layer 115 formed the underlayer 113. A protection layer 117 of amorphous carbon is provided on the magnetic layer 115.

sub B ~~The magnetic disk drive 100 described~~

2025-08-26

However, even during steady state operation, the magnetic head 120 may come into contact with the surface of the magnetic disk 110 due to unexpected affairs. To accommodate the continuous contact between the head 120 and the disk 110 when the drive starts or stops and the intermittent contact between the head 120 and the disk 110 when the head collides with unexpected affairs, the surface of the magnetic disk 110 should have both a low coefficient of friction and a high resistance to abrasion.

3. B⁴

In the near future, still lower spacing between the magnetic head 120 and the surface of the magnetic disk 110 will be required for high-density recording. Thus, it is really important to keep the surface of the magnetic disk 110 with a low coefficient of friction, a high resistance to

abrasion and water repellency over a longer period of time.

However, the inside of the magnetic disk drive 100 becomes high temperature. Furthermore, the magnetic disk 110 rotates at high speed in the drive 100. Even under the most benign ambient conditions, the interior of the disk drive 100 is a high-temperature environment due to the high rate of rotation of the disk 110 relative to the head 120. Increasing the rate of rotation of the disk 110 increases the centrifugal force that acts on any element of the lubrication layer 119; increasing the temperature of the disk 110 also increases the mobility of the elements of the lubrication layer 119. Elements of the lubrication layer 119 thus tend to move towards the circumference of the disk 110 over time, where they are more likely to be spun off the disk 110, so that the lubrication layer 119 tends to become thinner as the service time of the disk increases. A thinning lubrication layer 119 loses the capability of fulfilling its several roles. In order to prevent the lubrication layer 119 from losing the capability, the lubrication layer 119 should be formed by lubricant having strong adsorptive property to the surface (the protection layer 117) of the magnetic disk 110.

Concerning the lubrication layer 119 on the protection layer 117, it is considered that the lubrication layer 119 consists of a "bonding sub-layer" 119a, which consists of molecules that bind strongly to the protection layer 117, and a "mobile sub-layer" 119b, which consists of molecules that bind weakly to the protection layer 117. The mobile sub-layer 119b tends to undergo spin off as a result of centrifugal force by the disk rotation. It is estimated as a main reason of the thinning of the lubrication layer 119 as described above that the

mobile layer 119b tends to move to the circumferential part of the magnetic disk 110 and much mobile sub-layer 119b breaks away from the magnetic disk 110 in the end.

5 ^{3b5} In order to maintain the original thickness of the lubrication layer 119 as much as possible even the magnetic disk 110 used for a long period of time. Thinning of the lubrication layer 119 is associated with loss of the mobile sub-layer 119b.
10 Minimizing the thinning of the lubrication layer is accomplished by maximizing the "bonding ratio" of the lubrication layer, which is the ratio of the bonding sub-layer 119a to the mobile sub-layer 119b.

15 ^{3b6} Many prior arts attempted to increase the thickness of the bonding sub-layer 119a. By the prior arts, a lubricant is applied to the protection layer 117 of the magnetic disk 110, and a ultraviolet rays curing treatment or heating treatment is implemented on the lubrication layer
20 119 (lubricant) for increasing the ratio of the bonding sub-layer 119a (the bonding ratio).

However, it is not enough for increasing the bonding ratio to implement the above treatment only one time.

25

SUMMARY OF THE INVENTION

Accordingly, it is a general object of the present invention is to provide a novel and useful method of manufacturing a magnetic recording medium
30 in which the problems described above are eliminated. Another object of the present invention is to provide a magnetic medium manufactured by the method.

35 ^{3b7} The above objects are accomplished by a method of manufacturing a magnetic recording medium including steps of: a) laminating an underlayer, a magnetic layer for recording, and a protection layer of amorphous carbon on a substrate of the magnetic

recording medium in turn, and b) repeating a process to the protection layer of amorphous carbon comprising an application process of applying a lubricant, a subsequent ultraviolet rays treatment process, and a subsequent washing process for removing the lubricant which is not connected to the protection layer of amorphous carbon plural times, as claim 1 describes.

As claim 1 describes, the process to the protection layer of amorphous carbon comprising the application process of applying the lubricant, the subsequent ultraviolet rays treatment process, and the subsequent washing process for removing the lubricant which is not connected to the protection layer of amorphous carbon is repeated plural times. Thus, it is possible to reduce the ratio of the mobile sub-layer and increase the ratio of the bonding sub-layer by repeating plural times one set of the above three process.

That is, the combination power between a surface of the protection layer of amorphous carbon and the lubricant applied on the protection layer of amorphous carbon will be strengthen. On the other hand, the bonding sub-layer whose combination power with the protection layer of amorphous carbon will be removing by the subsequent wash process. Under the above state, it is easy to combine the lubricant with the surface of the protection layer of amorphous carbon because the lubricant is applied again. It is possible to increase the bonding ratio by repeating the process.

It is possible to either keep respective conditions for the above respective processes same and repeat the process or modify a condition. For instance, an irradiation time in the ultraviolet rays (UV) treatment process can be modified based on a forming state of the bonding sub-layer.

0041327 003404

It is difficult to know exactly the ratio of the mobile sub-layer and the bonding sub-layer in the lubrication layer formed on the protection layer of amorphous carbon. Accordingly, in the present invention, the magnetic recording medium on which the lubrication layer is formed is washed well by designated solvent and the lubrication layer implemented the wash process is regarded as the mobile sub-layer. Therefore, in the present invention, the increase of the bonding ratio means increase the width of the lubrication layer implemented the wash process.

36B" As claim 2 describes, it is preferred that the lubricant in the method as claimed in claim 1 is a compound of the perfluoro-polyether with an end-group including piperonyl or hydroxyl group. The bonding ration can be increase precisely by applying the lubricant which is a compound of the perfluoro-polyether with an end-group including piperonyl or hydroxyl group and implementing ultraviolet rays (UV) treatment process as a process to strengthen the combination with the protection layer of amorphous carbon.

As a liquid lubricant which is a compound that is a perfluoro-polyether with an end-group including piperonyl group, FOMBLIN AM2001 available from Ausimont corp and others, more preferably FOMBLIN AM3001, is applicable to be used. As a liquid lubricant which is a compound that is a perfluoro-polyether with an end-group including hydroxyl group, FOMBLIN Zdol2000 available from Ausimont corp and others, more preferably FOMBLIN AMZdol14000, is applicable to be used.

36B" The above objects are also accomplished by a method of manufacturing a magnetic recording medium including the steps of: a) laminating an underlayer, a magnetic layer for recording, and a

00913707.003104

5

15

20

25

30

~~As claim 6 describes, it is preferred that~~

the lubricant in the method as claimed in claim 5 is a compound of the perfluoro-polyether with an end-group including piperonyl or hydroxyl group.

1b16 Furthermore, the above object is also
5 accomplished by a method of manufacturing a magnetic recording medium including the steps of: a) laminating an underlayer, a magnetic layer for recording, and a protection layer of amorphous carbon on a substrate of the magnetic recording
10 medium in turn, and b) repeating a process to said protection layer of amorphous carbon comprising an application process of applying a lubricant, and a subsequent heat treatment process plural times, as claim 7 describes.

1b19 As claim 8 describes, it is preferred that
15 the lubricant in the method as claimed in claim 7 is a compound of the perfluoro-polyether with an end-group including hydroxyl group.

1b20 The other objects in the present invention
20 are to provide a magnetic recording medium having a lubricant layer comprising bonding sub-layer on a surface of the magnetic recording medium and manufactured by a process including the steps of a) laminating an underlayer, a magnetic layer for
25 recording, and a protection layer of amorphous carbon on a substrate of said magnetic recording medium in turn, and, b) repeating plural times a process to the protection layer of amorphous carbon comprising an application process of applying a
30 lubricant which is a compound of the perfluoro-polyether with an end-group including piperonyl or hydroxyl group, and a subsequent ultraviolet rays treatment process, or b) repeating plural times a
35 progress to the protection layer of amorphous carbon comprising an application process of applying a lubricant which is a compound of the perfluoro-polyether with an end-group including piperonyl or

00043787.003404

hydroxyl group, a subsequent ultraviolet rays treatment process, and a further subsequent washing process for removing said lubricant which is not connected to the protection layer of amorphous carbon, as claim 9 describes.

36321 The other objects in the present invention are to provide a magnetic recording medium having a lubricant layer including bonding sub-layer on a surface of said magnetic recording medium and manufactured by a process including the steps of a) laminating an underlayer, a magnetic layer for recording, and a protection layer of amorphous carbon on a substrate of the magnetic recording medium in turn, and, b) repeating plural times a process to the protection layer of amorphous carbon comprising an application process of applying a lubricant which is a compound of the perfluoro-polyether with an end-group including hydroxyl group, and a subsequent heat treatment process, or b) repeating plural times a progress to the protection layer of amorphous carbon comprising an application process of applying a lubricant which is a compound of the perfluoro-polyether with an end-group including hydroxyl group, a heat treatment process, and a further subsequent washing process for removing the lubricant which is not connected to said protection layer of amorphous carbon, as claim 10 describes.

Other objects and further of the present invention will be apparent from the following detailed description when read in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic diagram showing a relationship between a magnetic head and a rotating magnetic disk in the magnetic disk drive of the

present invention.

Fig. 2 is a diagram showing a step of an application process of applying a lubricant, an ultraviolet rays (UV) treatment process, and a washing process to the magnetic recording medium according to a first embodiment of the present invention.

Fig. 3 is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant, an ultraviolet rays (UV) treatment process, and a washing process plural times.

Fig. 4 is a diagram showing a step of the application process of applying a lubricant, a heat treatment process, and a washing process to the magnetic recording medium.

Fig. 5 is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant, a heat treatment process, and a washing process, plural times.

Fig. 6A is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I) and an ultraviolet rays (UV) treatment process (II) with a compound of the perfluoro-polyether with an end-group including piperonyl group as the lubricant; Fig. 6B is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I) and an ultraviolet rays (UV) treatment process (II) with a compound of the perfluoro-polyether with an end-group including hydroxyl group as the lubricant; and Fig. 6C is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I) and

2025 RELEASE UNDER E.O. 14176

a heat treatment process (II) with a compound of the perfluoro-polyether with an end-group including hydroxyl group as the lubricant.

58²²
DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

A description will be described, with reference to Figs. 2 through 6, of principles and embodiments of the present invention.

At first, a first embodiment of the present invention will be described. It is the first embodiment of the present invention to repeat plural times one set process of an application process of applying a lubricant, an ultraviolet rays (UV) treatment process, and a washing process to a protection layer of amorphous carbon on a magnetic recording medium.

Fig. 2 is a diagram showing a step of the application process of applying a lubricant, an ultraviolet rays (UV) treatment process, and a washing process to the magnetic recording medium.

1023 In the first embodiment of the present invention, a magnetic recording medium 1 manufactured by the prior art is prepared in advance. The magnetic recording medium 1 has a multilayered structure including a substrate, an underlayer formed on the substrate, and a magnetic layer formed on the underlayer. A protection layer of amorphous carbon is provided on the magnetic layer. The above-mentioned multilayered structure is the same as the prior arts shown in Fig. 1.

As Fig. 2 shows, in the present invention, at first the magnetic recording medium 1 is immersed in a bath of a liquid lubricant 4 filled in a container 40 and an application process (I) is implemented by a dip method for example. By the above process, the liquid lubricant 4 is applied on the protection layer of amorphous carbon which is a

09913787.002404

The liquid lubricant 4 is preferably a compound that is a perfluoro-polyether with an end-group including piperonyl group. The lubricant 4 may be a compound such as FOMBLIN AM3001 available from Ausimont corp. The liquid lubricant 4 is prepared by diluting the FOMBLIN AM3001 to roughly 0.05 wt % in fluorocarbon solvent such as FLORINATE FC-77 of Sumitomo 3M corp. The application process (I) by the dip method is implemented for 30 seconds as a dipped time and pulling the magnetic recording medium 1 from the bath at 2.3 mm per second for instance. The useful dipping method may not be limited, a known method such as spin-coating method and wiping method are available too.

Next, as Fig. 2 shows, a ultraviolet rays (UV) treatment process (II) is implemented to the lubrication layer 2 formed on the magnetic recording medium 1. By this process, it is possible to strengthen a combination power between the lubrication layer 2 and the protection layer of amorphous carbon. That is, it is possible to accelerate a change from a mobile sub-layer to a bonding sub-layer in the lubrication layer 2 and increase a bonding ratio.

30 16B24 In the ultraviolet rays (UV) treatment process (II), the UV wavelength of about 200nm and under is irradiated to the lubrication layer 2, the duration may be set to roughly 60 seconds. It is possible to combine two or more kinds of ultraviolet rays, whose wavelengths are about 254nm and 185nm for instance.

35 ~~16B2³~~ In Fig. 2 A shown in the light side of the container 40 roughly schematically shows a construction of the lubrication layer 2 on the magnetic recording medium 1. Thus, there are a lot

In order to solve the above state, a wash treatment (III) is implemented by immersing the magnetic recording medium 1 in a bath of a solvent for washing filled in a container 60, in the present embodiment. The mobile sub-layer 22 whose combination power with the protection layer of amorphous carbon is weak will be removed from the surface of the magnetic recording medium 1 by the wash process. Accordingly, it is possible to manufacture the magnetic recording medium 1 formed on its surface by the lubrication layer 2 comprised of only the bonding sub-layer 21 substantially, as B in the light side of the container 60 in Fig. 2 roughly schematically shows.

²⁴⁰
The fluorocarbon solvent which is same one for diluting the above lubricant can be used as the solvent 6 for washing in this embodiment. The useful fluorocarbon solvent may not be limited, and other solvent is available as long as it can remove the mobile sub-layer 22 from the surface of the magnetic recording medium 1. The wash process (III) is implemented for 30 seconds as a dipped time and pulling the magnetic recording medium 1 from the bath at 2.3 mm per second for instance.

*b Furthermore, it can be accelerated to remove the mobile sub-layer 22 from the surface of the magnetic recording medium 1 if the temperature of solvent 6 for washing is roughly less than the boiling point (at about 25 centigrade in case of said FLORINATE FC-77) and the magnetic recording medium 1 is washed by an ultrasonic generator in the wash process (III).

In the present embodiment, one set process of an application process of applying the lubricant (I), the ultraviolet rays (UV) treatment process (II), and the washing process (III) is repeated plural times. It is possible that the magnetic recording medium 1 has a designated width and to manufacture the magnetic recording medium 1 formed on its surface by a lubrication layer 2 (C1) comprised of only the bonding sub-layer 21 substantially, because the above process is repeated plural times. In case that the above process is repeated plural times, for instance five times, a lubrication layer 2 (C2) may be manufactured by omitting the last process, for instance the five times wash process (III). It is possible to either keep respective conditions for the above respective processes same and repeat the process or modify a condition. For instance, an irradiation time in the ultraviolet rays (UV) treatment process (II) can be modified based on a forming state of the bonding sub-layer.

Fig. 3 is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I), an ultraviolet rays (UV) treatment process (II), and a washing process (III) plural times. Fig. 3 shows widths of lubricant layer (widths of the bonding sub-layer substantially) measured after the surface of the magnetic recording

5 2.3 mm per second for instance.

10 layer in this case is about 1.25 nm.

20 lubricant layer increases about from 1.45 nm to 1.75 nm.

30 the washing process (III).

embodiment of the present invention. In this case, the lubricant 4 may be a compound such as FOMBLIN Zdol4000 available from Ausimont corp. The liquid

lubricant 4 is prepared by diluting the FOMBLIN Zdol4000 to roughly 0.05 wt % in fluorocarbon solvent such as FLORINATE FC-77 of Sumitomo 3M corp.

5 ~~328~~ Next, a second embodiment of the present invention will be explained based on Fig. 4 and 5. It is the second embodiment of the present invention to repeat plural times one set process of an application process of applying a lubricant, a heat treatment process, and a washing process to a protection layer of amorphous carbon on a magnetic recording medium. As contrasted with the first embodiment in which the ultraviolet rays (UV) treatment process is implemented, the heat treatment process is implemented in the second embodiment.

10 ~~329~~ Fig. 4 is a diagram showing a step of the application process of applying a lubricant, a heat treatment process, and a washing process to the magnetic recording medium. Same marks are put on parts corresponding to one in Fig. 2 showing the first embodiment.

15 ~~330~~ In the second embodiment of the present invention, a magnetic recording medium 1 manufactured by the prior art is prepared in advance as well as in the first embodiment. The magnetic recording medium 1 has the multilayered structure including a substrate, the underlayer formed on the substrate, and the magnetic layer formed the underlayer. The protection layer of amorphous carbon is provided on the magnetic layer.

20 ~~331~~ In the second embodiment of the present invention, at first the magnetic recording medium 1 is immersed in a bath of a liquid lubricant 41 filled in a container 40 and an application process (I) is implemented by a dip method for example.

25 ~~332~~ The liquid lubricant 41 is preferably a compound that is a perfluoro-polyether with an end-group including hydroxyl group. The lubricant 4 may

be a compound such as FOMBLIN Zdol4000 available from Ausimont corp. The liquid lubricant 41 is prepared by diluting the FOMBLIN Zdol4000 to roughly 0.05 wt % in fluorocarbon solvent such as FLORINATE FC-77 of Sumitomo 3M corp.

5 ~~1.2.3.4~~ The application process (I) by the dip method is implemented for 30 seconds as a dipped time and pulling the magnetic recording medium 1 from the bath at 2.3 mm per second for instance.
10 The useful dipping method may not be limited, a known method such as spin-coating method and wiping method are available too.

Next, as Fig. 4 shows, a heat treatment process (II) is implemented to the lubrication layer 2 formed on the magnetic recording medium 1. By this process, it is possible to strengthen a combination power between the lubrication layer 2 and the protection layer of amorphous carbon. That is, it is possible to accelerate a change from a mobile sub-layer to a bonding sub-layer in the lubrication layer 2 and increase the bonding ratio.

A constant temperature container 70 is used in the heat treatment process (II). The temperature inside of the constant temperature container 70 keeps at 100-120 centigrade. The magnetic recording medium 1 on which the lubrication layer 2 is formed is heated by keeping for about thirty minutes in the constant temperature container 70 in the second embodiment.

30 ~~1.2.3.5~~ A wash treatment (III) is implemented by immersing the magnetic recording medium 1 in a bath of a solvent 6 for washing filled in a container 6. The conditions for the wash treatment in the present embodiment are the same as one in the first
35 embodiment. It is possible to manufacture the magnetic recording medium 1 formed on its surface by the lubrication layer 2 comprised of only the

000413787.002404

bonding sub-layer 21 substantially according to the present embodiment.

In the present embodiment, one set process of an application process of applying the lubricant (I), the heat process (II), and the washing process (III) is repeated plural times. It is possible that the magnetic recording medium 1 has designated width and to manufacture the magnetic recording medium 1 formed on its surface by a lubrication layer 2 (C1) comprised of only the bonding sub-layer 21 substantially, because the above process is repeated plural times. In case that the above process is repeated plural times, for instance five times, a lubrication layer 2 (C2) may be manufactured by omitting the last process, for instance the five times wash process (III). It is possible to either keep respective conditions for the above respective process same and repeat the processes or modify a condition, a temperature for heat process (II) for instance, based on a forming state of the bonding sub-layer.

Fig. 5 is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I), the heat treatment process (II), and a washing process (III) plural times. Fig. 5 shows widths of lubricant layer (widths of the bonding sub-layer substantially) measured after the surface of the magnetic recording medium is washed by the solvent for washing as well as Fig. 3 does.

In Fig. 5 a white circle shows a case in which the application process and the heat treatment process are implemented one time according to prior arts. The width of lubricant layer in this case is about 0.85 nm.

The respective black circles show the present invention. That is, they show respective

000413707 0002404

5 The respective black circles clearly show that the
more the number of repeating the one set process
increases, the more numbers of the width of the
lubricant layer increases about from 1.05 nm to 1.15
nm. That is, the more the number of the one set
0 process increases, the more numbers of the width of
the lubricant layer increases.

Undermentioned embodiments are cases to
15 manufacture the magnetic recording medium without
implementing the wash treatment (III) implemented in
the first and second embodiments.

25 ~~sub B41~~ In case of to repeat plural times one set
process of an application process of applying a
lubricant and an ultraviolet rays (UV) treatment
process, the wash treatment process (III) in the
first embodiment of the present invention is not
30 implemented and the magnetic recording medium 1 is
manufactured with same conditions as ones in the
first embodiment. Therefore, an explanation based
on figure of the process steps is omitted.

~~3456789~~ In case of to repeat plural times one set
35 process of an application process of applying a
lubricant and a heat treatment process, the wash
treatment process (III) in the second embodiment of

the present invention is not implemented and the magnetic recording medium 1 is manufactured with same conditions as ones in the second embodiment. Therefore, an explanation based on figure about
5 process steps is omitted.

Inventors of the present invention confirmed that it is possible to increase the width of the bonding sub-layer by repeating one set process of the application process of applying the
10 lubricant (I) and the ultraviolet rays (UV) treatment process or heat process (II) plural times without washing process (III).

Fig. 6 is a view showing a state that the bonding sub-layer is increasing by the present
15 embodiment which omits the wash treatment process.

More particularly, Fig. 6A is a view showing a state that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I) and
20 an ultraviolet rays (UV) treatment process (II) with a compound of the perfluoro-polyether with an end-group including piperonyl group as the lubricant; Fig. 6B is a view showing a state that the bonding sub-layer is increasing by repeating one set process
25 of an application process of applying a lubricant (I) and an ultraviolet rays (UV) treatment process (II) with a compound of the perfluoro-polyether with an end-group including hydroxyl group as the lubricant; and Fig. 6C is a view showing a state
30 that the bonding sub-layer is increasing by repeating one set process of an application process of applying a lubricant (I) and a heat treatment process (II) with a compound of the perfluoro-polyether with an end-group including hydroxyl group
35 as the lubricant.

Figs. 6A, 6B, and 6C show widths of lubricant layer (widths of the bonding sub-layer

09943787.002404

BP43

sub B4

32B45

56B44

16B47

35 In Fig. 6C a white circle shows a case in which the application process are implemented one time and the heat treatment process according to prior arts. The width of lubricant layer in this

4B48

5
10

15

20

25

35

medium forming the lubrication layer substantially comprised of at least 1nm or more widths of the bonding sub-layer on the protection layer of amorphous carbon, according to the present invention.

5 The present invention is not limited to these embodiments, but various variation and modifications may be made without departing from the scope of the present invention.

10 3bB49 It is possible to manufacture the magnetic recording medium forming the lubrication layer substantially comprised of at least 1nm or more widths of the bonding sub-layer on the protection layer of amorphous carbon, according to the present invention. Besides, it is possible to make a
15 desired width by properly selecting the number of times of the treatment process is repeated.

20 3bB50 Therefore, as compared with the lubricant layer of the magnetic recording medium in the prior arts, the lubrication layer can be maintained under a state of a low coefficient of friction for long period of time, because the width of the magnetic recording medium according to the present invention is thick and the reduction of the width of the lubrication layer is very little with time progress.

25

30

35

FOR OFFICIAL USE ONLY